

## SELECTION & SPECIFICATION DATA

<b>Type</b>	Fibered Asphalt Emulsion
<b>Description</b>	A sprayable fibrated blend of selected mineral fillers and emulsified asphalts that provides excellent protection against moisture vapor intrusion in porous substrates such as cement.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Water-based with low VOCs</li> <li>• Very stable - no settling or separation</li> <li>• Environmentally friendly</li> <li>• Worker friendly</li> <li>• Meets ASTM D1227 Type 2, Class 1</li> </ul>
<b>Uses</b>	<ul style="list-style-type: none"> <li>• Dampproofing</li> <li>• Adhesive for polystyrene insulation</li> <li>• Moisture barrier</li> </ul>
<b>Color</b>	Black
<b>Finish</b>	Matte
<b>Primer</b>	Self-priming
<b>Dry Film Thickness (DFT)</b>	20 – 30 mils per coat
<b>Solids Content</b>	50% by weight 48% by volume
<b>Maximum Dry Temperature Resistance</b>	300°F (149°C)
<b>Limitations</b>	Protect from freezing Not for immersion service

## SUBSTRATES & SURFACE PREPARATION

<b>All</b>	Substrate must be clean, dry and free of contaminants.
<b>Previously Painted Surfaces</b>	Consult with ErgonArmor Technical Service.

## SAFETY

<b>Safety</b>	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
---------------	--

<b>Ventilation</b>	Use in well ventilated areas.
--------------------	-------------------------------

## MIXING & THINNING

<b>Mixing</b>	Not required
---------------	--------------

<b>Thinning</b>	Generally not required. Product is thixotropic and will thin under shear. If a reduction in static viscosity is desired, agitate to thin. The addition of water is not recommended.
-----------------	---

<b>Ratio</b>	Single component
--------------	------------------

<b>Cleanup</b>	Tools and hands should be cleaned with soap and water before the emulsion sets. Dried material can be cleaned with mineral spirits. Spray equipment should be flushed with soapy water then fresh water for short periods of non-use. For longer periods of non-use, a final flush using mineral spirits is recommended.
----------------	--

## APPLICATION GUIDANCE

<b>Spray Application</b>	Ertech 2110 is designed for spray application using airless equipment.
--------------------------	--

<b>Airless Spray</b>	For best results under a wide variety of spray conditions, a 30:1 or higher ratio pump is recommended.
----------------------	--

<b>Tip Size</b>	A 0.029-inch orifice tip size is recommended.
-----------------	---

<b>Hose L/D</b>	200 ft (max) x 3/8-inch diameter
-----------------	----------------------------------

<b>Whip L/D</b>	6 ft (max) x 1/4-inch diameter
-----------------	--------------------------------

<b>Pump Packings</b>	PTFE/UHMWP packings in the spray pump are recommended.
----------------------	--

<b>Film Thickness</b>	A film thickness of up to 60 mils wet can be achieved on vertical surfaces without sagging.
-----------------------	---

<b>Brush/Roller</b>	Ertech 2110 can be brush or roller applied.
---------------------	---

<b>Temperature</b>	Use in temperatures of 50°F (10°C) or higher for best performance.
--------------------	--

<b>Dry-To-Touch</b>	2 – 4 hours at 77°F (25°C). Dry times are decreased with air movement over the coating.
---------------------	---

<b>Full Cure</b>	24 – 48 hours at 77°F (25°C). Cure times are decreased with air movement over the coating.
------------------	--

## PACKAGING, ESTIMATING & HANDLING

ITEM #	PACKAGING
M-2110-000-001	Bulk - LB
M-2110-005-001	Pail - 5 gallons
M-2110-053-001	Drum - 53 gallons

<b>Theoretical Coverage Rate</b>	770 square feet per gallon at 1 mil DFT
----------------------------------	---

<b>Storage &amp; Shelf Life</b>	Estimated shelf life is 6 months when stored in a dry area at 75°F (24°C). Actual shelf life may vary with storage conditions. Do not store below 50°F (10°C) or above 110°F (43°C). Protect from freezing. Do not store product outside. Store indoors.
---------------------------------	--

### TYPICAL PHYSICAL PROPERTIES

Density ASTM D1475-13	8.6 lbs/gal
Solids by weight ASTM D5201-05a	50%
Solids by volume ASTM D5201-05a	48%
Specific gravity	1.03
Dry-to-touch, 77°F (25°C) ASTM D5895-96	2 – 4 hours
Full Cure, 77°F (25°C)	24 – 48 hours
Viscosity, 77°F (25°C) plastic cone pen ASTM D2983-19	370 dmm
Resistance to oils, greases & solvents	Poor
VOC ASTM D3960-05	0.2 lbs/gal maximum

Rev 12/2021

#### **TERMS AND CONDITIONS OF SALE**

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see [ergonarmor.com](http://ergonarmor.com).

Division of Ergon Asphalt & Emulsions, Inc. | P.O. Box 1639, Jackson, MS 39215-1639 | 601-933-3381 Fax | 601-933-3595 Phone | 877-98ARMOR Toll-Free | [ergonarmor.com](http://ergonarmor.com)