

SELECTION & SPECIFICATION DATA

Type	Epoxy tile grout
Description	Penntrowel EZ Grout 100 is a 3 component tile and paver floor grout.
Uses	<ul style="list-style-type: none"> • Bakeries • Breweries and distilleries • Bottling plants • Meat and poultry processing plants • Pharmaceutical plants • Chemical process facilities
Features	<ul style="list-style-type: none"> • Superior water-cleanability during installation • Low viscosity - can penetrate narrow joints typical of 2-3 mm pre-spaced fully vitrified tiling systems • Ideal for hygienic process floors where control of antimicrobial growth is critical
Limitations	<ul style="list-style-type: none"> • Not suitable for vertical wall tile applications. • Not for use beyond its chemical resistance or thermal capabilities. Consult ErgonArmor with specific questions.

INSTALLATION GUIDANCE

Reference Specifications	CES-309 Installation of direct bond tile floors CES-311 Installation of Tufchem™ Tiling Systems
Installation Conditions	Penntrowel EZ Grout 100 is formulated for ideal handling at 70°F (21°C). Materials and substrate should be acclimated to the air temperature prior to installation, and the air temperature should be between 50°F (10°C) and 90°F (32°C) during installation and cure. Bricks or tiles must be clean, dry and neutral pH.
Ratio	1.0 resin: 0.36 hardener: 3.5 filler by weight 1.0 resin: 0.36 hardener by weight, liquids only 2.5 resin: 1.0 hardener by volume, liquids only
Mixing	Pour measured quantity of resin into clean, dry mixing vessel. Slowly add measured quantity of hardener to resin and mix thoroughly. For Tufchem Tiling System, spread catalyzed resin across tile joints in accordance with installation methods outlined in specification CES-311. For conventional grouting, add filler and mix until filler is thoroughly wetted and grout is creamy, free of lumps and trowelable.
Work Life	95 minutes spread time at 70°F (21°C) per ANSI A118.3, test 5.1. Work life is shorter at higher temperatures. A larger volume of mixed material will have a shorter work life than a smaller volume.
Cleanup	For wet grout, use water and “Dawn” dish soap or a citrus based cleaner. For gelled grout, use xylene or MEK.

CURE TIME

Brick or Tile Temperature	Initial Set	Full Cure
70°F (21°C)	7 hours	5 days

SAFETY

Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
Ventilation	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

PACKAGING & ESTIMATING

Product	Code	Packaging
Penntrowel Water	29442	43 lb (4.5 gal) pail
Cleanable Grout Resin	29418	4 x 7.1 lb (0.75 gal) can case
Clear	29575	509 lb (55 gal) drum
EZ Grout Hardener	29653	15.5 lb (1.9 gal) can
	29654	4 x 2.6 lb (0.31 gal) can case
	29655	410 lb (50 gal) drum
TTS Grout Fillers		
Medium Black	29468	50 lb bag
Fine Black	29469	50 lb bag
Medium Red	29468-R	50 lb bag
Fine Red	29469-R	50 lb bag
Medium Gray	28193	50 lb bag
Fine Gray	28192	50 lb bag
Penntrowel EZ Grout 100 Kit		
Red	29529	27.6 lb (2.5 gal/0.26 cu. ft.) 3-
Black	29530	component kit, packed inside a 5 gal pail

When used unfilled with power grouting equipment (Tufchem™ Tiling System), a 58.5 lb (6.4 gallon) unit of EZ Grout 100 consists of 1 x 43 lb (4.5 gal) pail of resin and 1 x 15.5 lb (1.9 gal) can hardener, and a 1,937 lb (215 gal) unit consists of 3 x 509 lb drums of resin and 1 x 410 lb drum of hardener.

A 139 lb (1.29 cu. ft.) unit of EZ Grout 100 consists of 1 case of 4 x 7.1 lb (0.75 gal) cans of resin, 1 case of 4 x 2.6 lb (0.31 gal) cans of hardener and 2 x 50 lb bags of fine filler, and a 209 lb (1.94 cu. ft.) unit consists of 1 x 43 lb pail of resin, 1 x 15.5 lb can of hardener and 3 x 50 lb bags of fine filler.

Theoretical Coverage Consumption will vary based on tile size and joint width. Consult estimating guide CES-145 for assistance or consult with ErgonArmor.

Storage & Shelf Life Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.

If there is any question with respect to the quality of the components check reactivity prior to use. For assistance consult with ErgonArmor.

TYPICAL PHYSICAL PROPERTIES

Property	Typical Value
Color	Mixed liquids: amber clear Filled: varies with filler color – black, red, gray
Density, ASTM C138	108 lb/ft ³ (1729 kg/m ³)
Compressive strength, ANSI A118.3 test 5.6, 7-day	>5,500 psi (41 MPa)
Bond to tile, ANSI A118.3 test 5.5	>1,000 psi (6.9 MPa)
Adhesion to concrete, ASTM C321	Exceeds strength of concrete
Tensile strength, ANSI A118.3 test 5.7	>1,500 psi (10.3 MPa)
Flexural strength, ASTM C580	>1,350 psi (9.3 MPa)

Rev 06/2020
TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.